

ProRox SL 930^{SA}**Semi rigid slab****Applications**

ProRox SL 930^{SA} is a semi rigid stone wool slab. A one-sided facing with fibreglass reinforced aluminium foil (Alu) or glass tissue is available upon request.

Compliance

ProRox SL 930^{SA} Slabs comply with the requirements as set by internationally recognized standards like CINI 2.2.01 and ASTM C612 Type IA and IB and II.

Installation guidelines

- Mechanically fix ProRox SL 930^{SA} using self-adhesive or welded pins. Due to the rigidity of the product, it can also be mounted in cassettes.
- In the case of aluminium foil facing, finish lengthwise and crosswise joints with a self-adhesive aluminium tape ($\geq 75\text{mm}$). When insulating objects colder than the ambient temperature, where there is a risk of condensation, the insulation should be provided with a vapour barrier. The insulation should be finished with a metal (e.g. aluminium), watertight covering.

Advantages

- Available in a wide range of thicknesses
- Semi-rigid product combined with aluminium foil or fibreglass coating provides a smart, smooth surface finish

Product properties

	Performance						Standard
Thermal Conductivity	Mean Temp (°C)	50	100	150	200	250	ASTM C177
	λ (W/mK)	0.039	0.047	0.054	0.064	0.075	
Nominal Density	60 kg/m ³						ASTM C303
Maximum Service Temperature	450°C						ASTM C411/C447
Linear Shrinkage	Less than 2% (at max service temperature)						ASTM C356
Reaction to Fire	EuroClass A1 Surface burning characteristics; Flame spread = passed, Smoke development = passed						EN 13501-1 ASTM E84
Chloride Content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795						ASTM C871 ASTM C692/C871
Moisture Absorption	Less than 1% weight						ASTM C1104/ C1104M
Water Absorption	Less than 1 kg/m ²						EN 1609

Note: All information and data for technical parameters are based on laboratory testing.